



20 Progress Drive  
Morrisville, PA 19067  
215-736-1126  
215-736-1128 [fax]

**Product Data Sheet**

**Product** ACR-1300MIRXG

**ColorRx®**

Biocompatible, high flow, medium impact acrylic resin for healthcare applications. Stabilized to provide improved color after gamma sterilization. Transmittance 92%. Haze 1.5%.

<b>PHYSICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	10/12/2011
Specific Gravity	ASTM D792/ISO 1183	1.17 g/cm <sup>3</sup>	
Melt Flow Rate 230 C / 3.8 kg	ASTM D1238/ISO1133	13 g/10 min	
Mold Shrinkage Linear Flow (0.125)	ASTM D955	0.3 - 0.6 in/in	
Water Absorption @ 24 hrs	ASTM D570/ISO 62	0.3 %	
<b>IMPACT</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Izod Impact Strength Notched (73 F) (-22 F)	ASTM D256 / ISO189/1A	0.6 ft-lb/in ft-lb/in	
<b>MECHANICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Tensile Strength @ Yield**	ASTM D638/ISO 527-2	6700 psi	
Tensile Strength @ Break**		psi	
Elongation @ Yield*		%	
Elongation @ Break*	ASTM D638/ISO 527-2	33 %	
Flexural Strength***		psi	
Flexural Modulus***	ASTM D790/ISO 178	350,000 psi	
<b>HARDNESS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Hardness			
<b>THERMAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
DTUL @ 264 psi Annealed	ASTM D648/ISO 75-2	178 °F	
<b>IGNITION CHARACTERISTICS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
UL File Number			
Flame Rating - UL			

\* % elongation values are calculated from the elongation of the entire bar at 2.0 in/min

\*\* Tensile strength values are calculated at 2.0 in/min

\*\*\* Flexural data is calculated at 2.0 in/min

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.

