

## TECHNICAL DATA AND PROCESS SHEET

---

### 13% PTFE LUBRICATED ACETAL HOMOPOLYMER

#### INLUBE POMHTF13

#### TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNIT</u>	<u>METHOD</u>
<b>PHYSICAL</b>			
SPECIFIC GRAVITY	1.49	-	ASTM D792
WATER ABSORPTION	0.2	%	ASTM D570
MOLD SHRINKAGE, FLOW 0.125"	1.8-2.3	%	ASTM D955
<b>MECHANICAL</b>			
TENSILE STRENGTH, BRK	8600	psi	ASTM D638
TENSILE ELONGATION (BRK)	10-20	%	ASTM D638
FLEXURAL MODULUS	380,000	psi	ASTM D790
IZOD IMPACT, NOTHCED	1.3	ft-lb/in	ASTM D256
<b>THERMAL</b>			
HDTUL @ 264 PSI	215	°F	ASTM D648
<b>ELECTRICAL</b>			
SURFACE RESISTIVITY	$>10^{17}$	Ohm/Sq	ASTM D257
<b>PROCESSING</b>			
DRYING TEMPERATURE	180	°F	
DRYING TIME	4	hrs	
MELT TEMPERATURE	390-410	°F	
MOLD TEMPERATURE	180-220	°F	
BACK PRESSURE	25-50	psi	
SCREW SPEED	30-60	rpm	
VENT DEPTH	0.0005-0.001	in	

REVISED: 1/11/11 DJV

<p>This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents</p>
---