

TECHNICAL DATA AND PROCESS SHEET

**VERY HIGH FLOW, MOLD RELEASE POLYCARBONATE/ABS ALLOY
 (LOCKED MEDICAL FORMULATION)**

INSTRUC PCABSVHFMRMD

TYPICAL PROPERTIES

| PROPERTY | VALUE | UNIT | METHOD |
|-----------------------------|-------------------|-------------|---------------|
| PHYSICAL | | | |
| SPECIFIC GRAVITY | 1.22 | - | ASTM D792 |
| MOLD SHRINKAGE, FLOW 0.125" | 0.5-0.7 | % | ASTM D955 |
| MECHANICAL | | | |
| TENSILE STRENGTH, BRK | 8,200 | psi | ASTM D638 |
| TENSILE ELONGATION | 5-7 | % | ASTM D638 |
| FLEXURAL MODULUS | 350,000 | psi | ASTM D790 |
| IZOD IMPACT, NOTCHED | 11.8 | ft-lb/in | ASTM D256 |
| IZOD IMPACT, UNNOTCHED | >41 | ft-lb/in | ASTM D4812 |
| ELECTRICAL | | | |
| VOLUME RESISTIVITY | >10 ¹⁷ | Ohm-cm | ASTM D257 |
| PROCESSING | | | |
| DRYING TEMPERATURE | 200 | °F | |
| DRYING TIME | 3-4 | hrs | |
| MAX MOISTURE CONTENT | 0.02 | % | |
| MELT TEMPERATURE | 475-510 | °F | |
| MOLD TEMPERATURE | 125-180 | °F | |
| BACK PRESSURE | 50-100 | psi | |
| SCREW SPEED | 40-70 | rpm | |
| VENT DEPTH | 0.001-0.002 | in | |

12/22/10 DJV

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents