

## TECHNICAL DATA AND PROCESS SHEET

---

### 20% GLASS FIBER REINFORCED POLYSULFONE

#### INSTRUC PSUGF20

#### TYPICAL PROPERTIES

PROPERTY	VALUE	UNIT	METHOD
<b>PHYSICAL</b>			
SPECIFIC GRAVITY	1.38	-	ASTM D792
WATER ABSORPTION	0.20	%	ASTM D570
MOLD SHRINKAGE, FLOW 0.125"	0.2-0.4	%	
<b>MECHANICAL</b>			
TENSILE STRENGTH, BRK	14,500	psi	ASTM D638
TENSILE ELONGATION	2-4	%	ASTM D638
FLEXURAL MODULUS	800,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	1.3	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	10-12	ft-lb/in	ASTM D256
<b>THERMAL</b>			
HDTUL @ 264 PSI	365	°F	ASTM D648
<b>ELECTRICAL</b>			
VOLUME RESISTIVITY	>10exp15	Ohm-cm	ASTM D257
<b>PROCESSING</b>			
DRYING TEMPERATURE	275	°F	
DRYING TIME	3-4	hrs	
CYLINDER TEMPERATURE	600-640	°F	
MELT TEMPERATURE	640	°F	
MOLD TEMPERATURE	300	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0015-0.003	in	

9/22/10 DJV

<p>This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents</p>
-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------