



20 Progress Drive
Morrisville, PA 19067
215-736-1126
215-736-1128 [fax]

Product Data Sheet

Product
NYA1000

Colorfast®

Nylon/ABS alloy with high ductility and excellent chemical resistance

PHYSICAL	Test Method	Typical Values, Units	1/24/2014
Specific Gravity	ASTM D792	1.07 g/cm ³	
Melt Flow Rate (260 C/3800g)	ASTM D1238	6 g/10 min	
Mold Shrinkage Linear Flow (0.125)	ASTM D955	.008 to .010 in/in	
Water Absorption @ 24 hrs	ASTM D570	1.1 %	
IMPACT	Test Method	Typical Values, Units	
Izod Impact Strength Notched (73 F) (-22 F)	ASTM D256	13 ft-lb/in ft-lb/in	
MECHANICAL	Test Method	Typical Values, Units	
Tensile Strength @ Yield**	ASTM D638	6000 psi	
Tensile Strength @ Break**	N/A	N/R psi	
Elongation @ Yield*	N/R	N/R %	
Elongation @ Break*	ASTM D638	280 %	
Flexural Strength***	ASTM D790	8300 psi	
Flexural Modulus***	ASTM D790	170000 psi	
HARDNESS	Test Method	Typical Values, Units	
Hardness (R-scale)	ASTM D785	90	
THERMAL	Test Method	Typical Values, Units	
DTUL @ 264 psi Unannealed (.250)	ASTM D648	158 °F	
IGNITION CHARACTERISTICS	Test Method	Typical Values, Units	
UL File Number			
Flame Rating - UL			

* % elongation values are calculated from the elongation of the entire bar at 2.0 in/min

** Tensile strength values are calculated at 2.0 in/min

*** Flexural data is calculated at 2.0 in/min

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.

