



20 Progress Drive  
 Morrisville, PA 19067  
 215-736-1126  
 215-736-1128 [fax]

Product Data Sheet

**Product** PPE-1000RX

**ColorRx®**

Biocompatible, modified Polyphenylene Ether with high flow for healthcare applications.

<b>PHYSICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	7/5/2012
Specific Gravity	ASTM D792	1.06 g/cm <sup>3</sup>	
Melt Flow Rate 280 C / 5.0 kg	ASTM D1238	9.2 g/10 min	
Mold Shrinkage Linear Flow (0.125)	ASTM D955	.005 - .007 in/in	
Water Absorption @ 24 hrs	ASTM D570	0.06 %	
<b>IMPACT</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Izod Impact Strength Notched (73 F) (-22 F)	ASTM D256	4.0 ft-lb/in ft-lb/in	
<b>MECHANICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Tensile Strength @ Yield**	ASTM D638	8400 psi	
Tensile Strength @ Break**	ASTM D638	7100 psi	
Elongation @ Yield*	ASTM D638	7.2 %	
Elongation @ Break*	ASTM D638	28 %	
Flexural Strength***	ASTM D790	10500 psi	
Flexural Modulus***	ASTM D790	383,000 psi	
<b>HARDNESS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Hardness R Scale	ASTM D785	119	
<b>THERMAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
DTUL @ 264 psi Unannealed, 0.126"	ASTM D648	244 °F	
<b>IGNITION CHARACTERISTICS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
UL File Number			
Flame Rating - UL			

\* % elongation values are calculated from the elongation of the entire bar at 2.0 in/min

\*\* Tensile strength values are calculated at 2.0 in/min

\*\*\* Flexural data is calculated at 2.0 in/min

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.

