

TECHNICAL DATA AND PROCESS SHEET

POLETHYLENE PERMANENTLY ANTI-STATIC

INELEC PEAS

TYPICAL PROPERTIES

PROPERTY	VALUE	UNIT	METHOD
PHYSICAL			
SPECIFIC GRAVITY	0.95	-	ASTM D792
MOLD SHRINKAGE, FLOW 0.125"	1.0-1.5	%	
MECHANICAL			
TENSILE STRENGTH, BRK	3800	psi	ASTM D638
FLEXURAL STRENGTH	5500	psi	ASTM D790
FLEXURAL MODULUS	135,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	1.2	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	NB	ft-lb/in	ASTM D256
ELECTRICAL			
SURFACE RESISTIVITY	10exp9-10exp11	Ohm/Sq.	ASTM D257
PROCESSING			
DRYING TEMPERATURE	170	°F	
DRYING TIME (not required)	2-4	hrs	
MELT TEMPERATURE	375	°F	
MOLD TEMPERATURE	100	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0005-0.001	in	

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making its own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents