

TECHNICAL DATA AND PROCESS SHEET

**25% CARBON FIBER REINFORCED, ELECTRICALLY CONDUCTIVE
 POLYPROPYLENE**

INELEC PPCF25

TYPICAL PROPERTIES

PROPERTY	VALUE	UNIT	METHOD
PHYSICAL			
SPECIFIC GRAVITY	1.02	-	ASTM D792
MOLD SHRINKAGE, FLOW 0.125"	0.3-0.4	%	ASTM D955
MECHANICAL			
TENSILE STRENGTH, BRK	5,600	psi	ASTM D638
FLEXURAL MODULUS	1,400,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	0.9	ft-lb/in	ASTM D256
IZOD IMPACT, UNNOTCHED	2.3	ft-lb/in	ASTM D4812
ELECTRICAL			
SURFACE RESISTIVITY	10 ² -10 ⁴	Ohm/Sq.	ASTM D257
PROCESSING			
DRYING TEMPERATURE	170	°F	
DRYING TIME (not required)	2-4	hrs	
MELT TEMPERATURE	380-440	°F	
MOLD TEMPERATURE	100	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0005-0.001	in	

3/2/12 TSC

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents