

## TECHNICAL DATA AND PROCESS SHEET

---

### 10% CARBON FIBER FILLED POLYSULFONE

#### INELEC PSUCF10

#### TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNIT</u>	<u>METHOD</u>
<b>PHYSICAL</b>			
SPECIFIC GRAVITY	1.28	-	ASTM D792
MOLD SHRINKAGE, FLOW 0.125"	0.3-0.4	%	ASTM D955
<b>MECHANICAL</b>			
TENSILE STRENGTH, BRK	14,000	psi	ASTM D638
TENSILE ELONGATION	2 - 3	%	ASTM D638
FLEXURAL MODULUS	1,000,000	psi	ASTM D790
IZOD IMPACT, NOTCHED	1.8	ft-lb/in	ASTM D256
<b>THERMAL</b>			
HDTUL @ 264 PSI	360	°F	ASTM D648
<b>ELECTRICAL</b>			
SURFACE RESISTIVITY	$10^2$ - $10^6$	Ohm/sq	ASTM D257
<b>PROCESSING</b>			
DRYING TEMPERATURE	275	°F	
DRYING TIME	3-4	hrs	
CYLINDER TEMPERATURE	620-700	°F	
MELT TEMPERATURE	640-660	°F	
MOLD TEMPERATURE	300	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	
VENT DEPTH	0.0015-0.003	in	

11/28/11 DJV

<p>This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents</p>
---