

**TECHNICAL DATA AND PROCESS SHEET**

**30% GLASS FIBER REINFORCED 15% PTFE LUBRICATED PBT**

**INLUBE PBTGF30TF15**

**TYPICAL PROPERTIES**

PROPERTY	ASTM METHOD	English		Metric SI	
		English	UNITS	Metric SI	UNITS
<b>GENERAL</b>					
SPECIFIC GRAVITY	D792	1.64		1.64	
SPECIFIC VOLUME		16.89	in <sup>3</sup> /lb	0.610	cm <sup>3</sup> /gm
WATER ABSORPTION (24 Hrs)	D570	0.04	%	0.04	%
MOLD SHRINKAGE	D955	0.1-0.2	%	0.1-0.2	%
<b>MECHANICAL</b>					
TENSILE STRENGTH	D638	15,500	psi	107	MPa
ELONGATION, YIELD	D638	2-4	%	2-4	%
FLEXURAL STRENGTH	D790	23,000	psi	159	MPa
FLEXURAL MODULUS	D790	1,300,000	psi	8,963	MPa
SHEAR STRENGTH	D732				
IZOD IMPACT STRENGTH	D256				
NOTCHED 1/8"		1.5	ft.lb./in.	80	J/m
UNNOTCHED 1/8"		14	ft.lb./in.	746	J/m
ROCKWELL HARDNESS					
<b>THERMAL</b>					
HDTUL	D648	425	°F	218	°C
@ 264 PSI					
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	1.3	in./in. F x10 <sup>-5</sup>	2.34	mm/mm C 10 <sup>-6</sup>
FLAMMABILITY <sup>1</sup>	U.L.Subj 94	HB@1/16	in	HB@ 1.5	mm
<b>ELECTRICAL</b>					
SURFACE RESISTIVITY		10e <sup>16</sup>	ohms/sq	10e <sup>16</sup>	ohms/sq
<b>PROCESSING</b>					
DRYING TEMPERATURE		230	°F	110	°C
DRYING TIME		4	hrs	4	hrs
MELT TEMPERATURE		430-500	°F	220- 260	°C
MOLD TEMPERATURE		225	°F	107	°C
BACK PRESSURE		50-100	psi	0.3 - 0.7	MPa
SCREW SPEED		40-70	rpm	40-70	rpm
VENT DEPTH		0.0015-0.003	in	0.038 - 0.075	mm

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents.