

TECHNICAL DATA AND PROCESS SHEET

20% TEFLON LUBRICATED HEAT STABILIZED POLYPROPYLENE BASED ON FDA COMPLIANT RAW MATERIALS

INLUBE PPTF20HSLE

TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>VALUE</u>	<u>UNIT</u>	<u>METHOD</u>
PHYSICAL			
SPECIFIC GRAVITY	1.03	-	ASTM D792
WATER ABSORPTION	0.02	%	ASTM D570
MOLD SHRINKAGE, FLOW 0.125"	1.8-2.3	%	
MECHANICAL			
TENSILE STRENGTH, BRK	4,200	psi	ASTM D638
FLEXURAL STRENGTH	6,450	psi	ASTM D790
FLEXURAL MODULUS	230,000	psi	ASTM D790
IZOD IMPACT, NOTHCED	0.5	ft-lb/in	ASTM D256
THERMAL			
HDTUL @ 264 PSI	140	°F	ASTM D648
ELECTRICAL			
SURFACE RESISTIVITY	10exp17	Ohms/Sq	ASTM D257
PROCESSING			
DRYING TEMPERATURE	170	°F	
DRYING TIME (not required)	2-4	hrs	
MELT TEMPERATURE	380-440	°F	
MOLD TEMPERATURE	100-150	°F	
BACK PRESSURE	50-100	psi	
SCREW SPEED	40-70	rpm	

This information is based on our experience to date and we believe it to be reliable. It is intended only as a guide for use at your discretion and risk. We cannot guarantee favorable results and assume no liability in connection with its use of the products described. Each user bears full responsibility for making it's own determination as to the suitability of the product described. None of this information is to be taken as a license to operate under, or recommendation to infringe any patents