



20 Progress Drive  
 Morrisville, PA 19067  
 215-736-1126  
 215-736-1128 [fax]

Product Data Sheet

**Product** NY2-1000RX

**ColorRx®**

Biocompatible, lubricated nylon 6,6 approved for healthcare applications.

<b>PHYSICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	6/15/2010
Specific Gravity	ASTM D792	1.14 g/cm <sup>3</sup>	
Shrinkage, linear, .08", Dry	ASTM D955	0.14 g/10 min	
Shrinkage, transv., .08", Dry	ASTM D955	0.14 g/10 min in/in	
Water Absorption @ 24hrs	ASTM D570	1.2 %	
<b>IMPACT</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Izod Impact Strength, notched 1/8", 73F, Dry / 1/8", 73F, Conditioned	ASTM D256	ft-lb/in 0.9 / 2.0 ft-lb/in	
<b>MECHANICAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
Tensile Strength @ Yield, Dry, 73F	ASTM D638	11800 psi	
% Elongation @ Break, Dry, 73F	ASTM D638	psi 60 % %	
Flexural Modulus, Dry, 73F	ASTM D790	405,000 psi psi	
<b>HARDNESS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
<b>THERMAL</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	
DTUFL, Dry 66 psi, unannealed 264 psi, unannealed = 145F	ASTM D648	400 °F	
<b>IGNITION CHARACTERISTICS</b>	<b>Test Method</b>	<b>Typical Values, Units</b>	

\* % elongation values are calculated from the elongation of the entire bar at 2.0 in/min

\*\* Tensile strength values are calculated at 2.0 in/min

\*\*\* Flexural data is calculated at 2.0 in/min

The values shown are typical values that have been obtained using test bars molded from laboratory samples and are not intended for specification purposes. These values are for natural colors only. Addition of pigments may alter some values. Inasmuch as LTL Color Compounders has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own test to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any LTL Color Compounders patent covering such use or as recommendations for use of such materials in the infringement of any patent. These are developmental products with estimated physical property profiles. Actual values will need to be determined upon production of material.

